## Sedur Fix F SP seals polyethylene with PVC surface

| PVC surface protection  | Data   |
|-------------------------|--|
| colors                  | white, anthracite, brown                                   |
| thickness               | 300 μm   |
| hardness                | 47 +/- 2 Shore D   |
| Polyethylene (core)     | Data   |
| color                   | anthracite   |
| volume weight           | ca. 35 kg/m3   |
| temperature resistance  | -60°C until 80°C   |
| compressive stress      | at 10% deformation ca. 2,0 N/cm2                           |
|                         | at 25% deformation ca. 4,0 N/cm2                           |
|                         | at 40% deformation ca. 8,0 N/cm2                           |
| UV-resistance           | largely stable   |
| reaction to fire        | flammable according to DIN 4102 class (B3)                 |
| water absorption        | ca. 5 Vol%   |
| chemical resistance     | chlorinated solvents conditionally stable                  |
|                         | saltwater resistant  |
|                         | gasoline resistant   |
|                         | heating oil resistant                                      |
|                         | caustic soda resistant                                     |
|                         | hydrochloric acid 10% resistant                            |
|                         | sulfuric acid 30% resistant                                |
| Adhesive                | Data   |
| adhesive / cover        | acrylic, modified (waterproof) / polyethylene paper, white |
| thickness               | 0.12 mm  |
| temperature range       | -60°C until +120°C   |
| shear strength on steel | (N/625 mm2) +23°+/-2°C 40 DIN EN 1943                      |
| peel strength on steel  | (N/25 mm2) +23°+/-2°C 35 DIN EN 1939                       |

The technical information reflects our current knowledge and experience. Special conditions in special individual cases in the application must be taken into account depending on the situation. All values are mean unless otherwise stated.

We are at your disposal for further questions about our products.

